

STONE EFFECT PORCELAIN



5

COLOURS

4

SIZES

2

FINISH




12/19%

A collection inspired by the volcanic power of granite, Royan is available in two versions, fine-grained and rough-grained, both in matt and semi-polished finishes. Also available is the Cage décor with a regular pattern of vertical and horizontal lines interrupted by diagonal slashes.


## COLOURS AVAILABLE




DARK FINE GRAIN



GREY FINE GRAIN



WHITE FINE GRAIN



SAND FINE GRAIN



TAUPE FINE GRAIN




WHITE ROUGH GRAIN



SAND ROUGH GRAIN



TAUPE ROUGH GRAIN



DARK ROUGH GRAIN



GREY ROUGH GRAIN


## Cage Tiles




Dark




Grey




White




Sand




Taupe




Dark Mosaic




White Mosaic



Sand Mosaic



Taupe Mosaic



Grey Mosaic

# PARKSIDE

## PRODUCT DATA SHEET

ROYAN



PORCELAIN	Fine Grain 10mm Thick			Rough Grain 10mm Thick			Mosaic 10mm Thick		Cage 10mm Thick		Wall/ Floor	Interior / Exterior
	Matt	Semi Polished	Structure d	Matt	Semi Polished	Structure d	Matt	Semi Polished	Matt	Semi Polished	All Tiles	All Tiles
300 x 300							✓	✓			Wall & Floor	Interior
300 x 600	✓	✓	✓	✓	✓	✓					Wall & Floor	Interior
900 x 900	✓	✓		✓	✓						Wall & Floor	Interior
600 x 1200	✓	✓	✓	✓	✓	✓			✓		Wall & Floor	Interior

Group

Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	≤ 0.5 %
Breaking strength	ISO 10545-4	≥ 1300N	Ave ≥ 2000N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm <sup>2</sup>	Ave ≥ 50 N/mm <sup>2</sup>
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	≤175mm <sup>2</sup>	≤175mm <sup>2</sup>
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	UHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV	Recycled Content	
				%
Rough Grain Structured	✓	✓	10mm options	12%
			20mm options	19%

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential