

PARKSIDE

HOPPER

CONCRETE EFFECT TILES



3

COLOURS

4

SIZE

2

FINISH

0

SPECIAL PIECES

Hopper concrete is one of Parkside's favourite porcelain concrete effects. Unlike other glazed porcelain tiles, Hopper is a full bodied tile with the aggregate porcelain pieces running throughout the body of the tile, not just on the surface, meaning that it really does offer a credible alternative to poured concrete floors. The matt and semi polished finishes are easy to clean so are great for interiors.



PORCELAIN	10.5mm Thick		Wall/Floor
	Matt	Semi Polished	All Tiles
300 x 600	✓	✓	Wall & Floor
600 x 600	✓	✓	Wall & Floor
600 x 1200	✓	✓	Wall & Floor
1200 x 1200	✓	✓	Wall & Floor

Group

Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave ≤ 0.1 %
Breaking strength	ISO 10545-4	≥ 1300N	Ave ≥ 6500N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	Ave 45 N/mm ²
Resistance to deep abrasion	ISO 10545-6	≤ 175mm ²	Ave ≤ 140mm ²
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	UHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULB
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential