



4

COLOURS

1

SIZE

1

FINISH

0

SPECIAL PIECES

Etilage consists of wood-effect porcelain tiles in a format designed to guarantee added value by bringing out the full beauty of its design while also allowing for continuity. The tiles feature a gentle relief texture that emulates sawn timber, lending added warmth to surfaces.

The 1510x240mm plank has 30 patterns within each colour option for a natural realism.

COLOURS AVAILABLE



BROWN SLIP RESISTANT

TAUPE SLIP RESISTANT

HONEY SLIP RESISTANT

MAPLE SLIP RESISTANT

PORCELAIN	11mm Thick	Wall/Floor	Interior/ Exterior
	Matt	All Tiles	All Tiles
1510x240	✓	Wall & Floor	Interior & Exterior

Group

Bla – Porcelain

ETILAGE

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	≤ 0.5 %
Breaking strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm2	Ave Minimum 35 N/mm2
Resistance to surface abrasion	ISO 10545-7	Declare Class	Brown, Taupe & Maple – PEI 3 Honey – PEI 4
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
Full Range	✓	✓

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential