

PARKSIDE

Monroe

Concrete & Wood effect Collection



10% / 12%

6

COLOURS

1

SIZE

1

FINISH

0

SPECIAL PIECES

The Monroe range is made to please the most demanding designers and architects, with a combination of concrete, gloss, wood and mosaic options. The most extraordinary combinations can be created thanks to the assortment of 8 colour variations, 4 warm tones and 4 cold – different patterns are never repeated over around 10m2 of product, producing original design schemes. This range is also available in 12 different sizes, ideal for designing large and small surfaces.

COLOURS AVAILABLE

 <p>White</p>		 <p>Smoke</p>	
 <p>Ivory</p>		 <p>Taupe</p>	
 <p>Sand</p>		 <p>Brown</p>	
 <p>Grey</p>		 <p>Black</p>	

PARKSIDE

Monroe

Concrete & Wood effect Collection

SIZE GUIDE

Wood

250x1800mm

200x1800mm

200x1200mm



Concrete

600x600mm

300x600mm

1200x1200mm

900x900mm

60x250mm

125x250mm

800x1800mm

PARKSIDE

PRODUCT DATA SHEET

Monroe



Dimensions	Multiple
Finish	Matt
Body	Porcelain
Wall/Floor	Wall & Floor
Group	Bla
Pendulum Dry (4S)	36+
Pendulum Wet (4S)	25-35
Pendulum Wet (TRL)	Tbc

Available Sizes
60x250mm
125x250mm
300x600mm
600x600mm
900x900mm
1200x1200mm
800x1800mm
250x1800mm
200x1800mm
200x1200mm

Recycled Content	%
1200x1200 10mm	10%
All other 10mm size options	12%

	Standard	Requirement	Typical Test Value
Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
Thickness	ISO 10545-2	$\pm 5\%$ $\leq \pm 0.5\text{mm}$	Pass
Straightness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 1.5\text{mm}$	Pass
Flatness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
Rectangularity	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
Modulus of rupture	ISO 10545-4	35 N/mm ² Average min	Pass
Resistance to surface abrasion	ISO 10545-7	Max 17mm ³	Pass
Frost Resistance	ISO 10545-12	Complies with Standard	Pass
Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
Resistance to Stain	ISO 10545-14	Min class 3	Pass
Resistance to chemicals	ISO 10545-14	Min Class B	Pass
Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential