

PARKSIDE

ENZ02

CONCRETE, MARBLE & WOOD EFFECT TILES



Beton one
The Ash, Greige and Plum options have 71% recycled content and Chalk 31%.

Wood one
The Brown, Mahogany and Nut options have 71% recycled content and Honey and White 31%.



Marble one
31% recycled content.

14

COLOURS

2

SIZES

2

FINISHES

0

SPECIAL PIECES

Enz02 includes 3 separate ranges; Beton one, Marble one and Wood one.

Totalling a combined 14 colours, 2 sizes and 2 finishes please use the below table as a reference guide.

PORCELAIN

	9mm Thick		Wall/Floor	Interior/ Exterior
	Matt	Gloss	All Tiles	All Tiles
600X600 Beton one	✓		Wall & Floor	Interior & Exterior
600X600 Marble one		✓	Wall & Floor	Interior & Exterior
200x1200 Wood one	✓		Wall & Floor	Interior & Exterior

Group

Bla – Porcelain

MARBLE ONE

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	$E_b \leq 0.5\%$	Ave 0.08%
Breaking strength	ISO 10545-4	$\geq 1300N$	Ave 2500 N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	Ave Minimum 35 N/mm ²
Resistance to surface abrasion	ISO 10545-7	Declare Class	GLOSSY – Calacatta & Calacatta Gold – PEI 4, Greek White, Volakas, Dolomite – PEI 5
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	Glossy – GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

Group

Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.08 %
Breaking strength	ISO 10545-4	≥ 1300N	Ave 2500N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm2	Ave 50 N/mm2
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	≤175mm2	Ave ≤140mm2
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	Class UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA
Resistance to Stain	ISO 10545-14	Declare Value	Class 4
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential