



12

COLOURS

1

SIZE

1

FINISH

0

SPECIAL PIECES

The Dalrae collection interprets the traditional appearance of the brick, presented in 12 modern solid colours. The glossy finish enriches the surface nuances.

Available in porcelain and 250x60mm, Dalrae is suitable to be used on both walls and floors, making it able to adapt to commercial as well as residential solutions.

IN THIS RANGE



WHITE



ALMOND



BEIGE



LIGHT GREY



GREY



TAUPE



LIGHT BLUE



MUSK



COPPER



BRONZE



DARK GREY



BLACK

PORCELAIN

6mm Thick

Wall/Floor

Interior/Exterior

Matt

All Tiles

All Tiles

250x60

✓

Wall & Floor

Interior & Exterior

Group

Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.2%
Breaking strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	Ave Minimum 35 N/mm ²
Resistance to surface abrasion	ISO 10545-7	Declare Class	PEI 3 – Black, Bronze, Iron & Copper PEI 4- Taupe, Grey, Light Blue, Dark Grey, Musk & Light Grey PEI 5 - Beige, White & Almond
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
	✓	

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential