



9

COLOURS

1

SIZE

2

FINISHES

0

SPECIAL PIECES



0%

The Fenman collection leans toward the more traditional aesthetic with rustic edges, colour variation and undulated surfaces but features a modern twist with the curved 3D tile options. All colours are available in a gloss finish with the Calc 3D also available in a matt finish.

This range contains 0% recycled content.

	10mm Thick	20mm Thick	Wall/Floor	Interior/Exterior
PORCELAIN	Gloss	Gloss	All Tiles	All Tiles
50X250	✓	✓	Wall	Interior

PARKSIDE

FENMAN

CERAMIC WALL TILES

IN THIS RANGE:



CALC MATT 3D

CALC GLOSS 3D

ROSE 3D

AQUA 3D



ASH 3D

TURCHESE 3D

GREY 3D

OLIVE 3D



BONE

CAPPUCCINO

ASH

ROSE



AQUA

TURCHESE

OLIVE

GREY

Group	BIII - Ceramic
-------	----------------

	Standard	Requirements	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb >10%	Ave 13.5%
Breaking strength	ISO 10545-4	≥ 600N	NPD
Modulus of rupture	ISO 10545-4	Ave Minimum 12 N/mm2	NPD
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Not Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Min Class 3	Class 3
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Recycled Content	%
Fenman	0%

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential