

PARKSIDE

GOPSAL

BRICK TILES



8

COLOURS

1

SIZE

1

FINISH

0

SPECIAL PIECES




0%


A versatile collection which simultaneously offers both an elegant and cosmopolitan atmosphere.

This extruded porcelain collection features a smoky effect which creates movement and dimension in 8 unique colours.


This range has 0% recycled content.




Grey




Rose




Ivory




Terracotta




Carbon



Blue



Green



Dark Grey

PORCELAIN

8mm Thick

Wall/Floor

Interior/Exterior

Matt

All Tiles

All Tiles

72x295

✓

Wall & Floor

Interior & Exterior

Group

Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.1%
Breaking strength	ISO 10545-4	≥ 1300N	Ave ≥ 1300N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	Ave Minimum 35 N/mm ²
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	≤175mm ²	Ave ≤175mm ²
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	UHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to Stain	ISO 10545-14	Declare Value	Class 4
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Recycled Content	%
Gopsal	0%

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential