

# PARKSIDE

## SENSI

### STONE EFFECT TILES



10mm options in Brown and Grey - 41.9%  
 10mm options in Taupe - 12.7%  
 10mm options in Ivory and White - 7.1%  
 20mm options - 12.5%  
 6mm slabs - 7.1%

5

COLOURS

6

SIZES

2

FINISHES

0

SPECIAL PIECES

Inspired by the different textures of earth, Sensi has been designed by Italian architect and designer Matteo Thun. Available in five neutral shades, the collection remind us of the strength of nature.

Developed with close attention to environmental impact, Sensi uses recycled content and sustainable production processes with self-generated electricity and water recycling.

PORCELAIN	10mm Thick				6mm Thick			20mm	Wall/Floor or	Interior	
	Matt R9	Matt R10	Matt R11	Matt PTV	Matt R9	Matt R10	Matt R11	Matt PTV	Matt R11	All Tiles	All Tiles
60x120	✓	✓	✓	✓	✓	✓		✓	✓		
80x80	✓	✓	✓	✓							
40x80	✓	✓	✓	✓						Wall & Floor	Interior
120x120					✓	✓		✓			
120x240					✓	✓					
120x280					✓	✓		✓			

# PARKSIDE

SENSI

STONE EFFECT TILES

IN THIS RANGE




WHITE LITHOS

WHITE FOSSIL

IVORY LITHOS

IVORY FOSSIL



GREY LITHOS

GREY FOSSIL

TAUPE LITHOS

TAUPE FOSSIL




BROWN LITHOS

BROWN FOSSIL

BROWN DUST

BROWN SAND




TAUPE DUST

TAUPE SAND

GREY DUST

GREY SAND



IVORY DUST

IVORY SAND

WHITE DUST

WHITE SAND

<b>Group</b>	Bla - Porcelain
--------------	-----------------

	Standard	Requirements	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.08%
Breaking strength	ISO 10545-4	≥ 1300N	Ave 14000N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm <sup>2</sup>	Ave 52 N/mm <sup>2</sup>
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm <sup>3</sup>	Ave 140mm <sup>3</sup>
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA
Resistance to Stain	ISO 10545-14	Declare Value	Class 4
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

<b>Group</b>	Bla - Porcelain
--------------	-----------------

	Standard	Requirements	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.08%
Breaking strength	ISO 10545-4	≥ 1300N	≥ 3200N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm2	Ave 50 N/mm2
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm3	Ave 140mm3
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA
Resistance to Stain	ISO 10545-14	Declare Value	Dust Fossil – Class 5 Sand, Fossil and Lithos – Class 4
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

Group	Bla - Porcelain		
	Standard	Requirements	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.08%
Breaking strength	ISO 10545-4	≥ 1300N	≥ 1350N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm <sup>2</sup>	Ave 52 N/mm <sup>2</sup>
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm <sup>3</sup>	Ave 140mm <sup>3</sup>
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA
Resistance to Stain	ISO 10545-14	Declare Value	MATTE – Class 5 LITHOS & SAND – Class 4
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Recycled Content	%
10mm Brown & Grey	41.9%
10mm Taupe	12.7%
10mm Ivory & White	7.1%
20mm Options	12.5%
6mm Slabs	7.1%

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential