

PARKSIDE

RANDOLPH

MARBLE EFFECT PORCELAIN RANGE



11%

3

COLOURS

1

SIZE

1


FINISH

0

SPECIAL PIECES

Randolph is a beautiful collection of porcelain hexagonal tiles. The matt, marble effect range is available in 3 monochrome colours and has a realistic likeness to marble.

COLOURS AVAILABLE



Black




Grey



White

SIZE GUIDE

210x182 at its largest points
0.03m² coverage



PARKSIDE

PRODUCT DATA SHEET

RANDOLPH



Dimensions	210x182x9mm
Finish	Matt
Body	Porcelain
Wall/Floor	Wall & Floor
Group	Bl _a
Pendulum Dry (4S)	36+
Pendulum Wet (4S)	0-24
Pendulum Wet (TRL)	0-24

Available Sizes
210x182x9mm

Recycled Content	%
Randolph	11%

	Standard	Requirement	Typical Test Value
Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
Thickness	ISO 10545-2	$\pm 5\%$ $\leq \pm 0.5\text{mm}$	Pass
Straightness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 1.5\text{mm}$	Pass
Flatness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
Rectangularity	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
Modulus of rupture	ISO 10545-4	35 N/mm ² Average min	Pass
Resistance to surface abrasion	ISO 10545-7	$\leq 175\text{mm}^3$	120-150
Frost Resistance	ISO 10545-12	Complies with Standard	Pass
Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
Resistance to Stain	ISO 10545-14	Min class 3	Pass
Resistance to chemicals	ISO 10545-14	Min Class B	Pass
Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential