

# PARKSIDE

# TYNE



## BRICK EFFECT COLLECTION



9

COLOURS

1

SIZE

1

FINISH


0

SPECIAL PIECES

Create a traditional brick and mortar aesthetic with these brick format tiles. Suitable for wall and floor the Tyne collection is available in 4 earthy, natural colours with 48 variations to give it its realistic appearance.

## COLOURS AVAILABLE

### Natural



White



Sand



Mud



Grey



Multi



Old Red


### Coloured



Baltic




Baltic Shade




Balene



Balene Shade



Bracco



Bracco Shade

## SIZE GUIDE

60x250mm



TYNE

Dimensions	60x250x10mm
Finish	Structured
Body	Porcelain
Wall/Floor	Wall & Floor
Group	BI <sub>a</sub>
Pendulum Dry (4S)	36+
Pendulum Wet (4S)	36+
Pendulum Wet (TRL)	36+

Available Sizes
60x250x10mm

Recycled Content	%
Tyne	40%

	Standard	Requirement	Typical Test Value
Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
Thickness	ISO 10545-2	$\pm 5\%$ $\leq \pm 0.5\text{mm}$	Pass
Straightness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 1.5\text{mm}$	Pass
Flatness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
Rectangularity	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
Modulus of rupture	ISO 10545-4	35 N/mm <sup>2</sup> Average min	Pass
Resistance to surface abrasion	ISO 10545-7	n/a	PEI 5
Frost Resistance	ISO 10545-12	Complies with Standard	Pass
Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
Resistance to Stain	ISO 10545-14	Min class 3	Pass
Resistance to chemicals	ISO 10545-14	Min Class GB	Pass
Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential