

PARKSIDE

BOOM

CONCRETE EFFECT TILE, RANGO



5

COLOURS

4

SIZES

2

FINISHES

0

SPECIAL PIECES

Boom with its strong, forthright character that gives personality to interior design. The two surface finishes for indoor/outdoor use provide an attractive visual continuity. The deep colours are designed to dialogue with trendy public locations.

PORCELAIN	9,5mm Thick		10mm Thick		10,5mm Thick		Wall/Floor	Interior/ Exterior	
	Matt	Structured	Matt	Structured	Matt	Structured	All Tiles	All Tiles	
300 x 600	✓	✓						Wall & Floor	Interior & Exterior
600 x 600	✓	✓						Wall & Floor	Interior & Exterior
750 x 750			✓				Wall & Floor	Interior & Exterior	
750 x 1500					✓		Wall & Floor	Interior & Exterior	


COLOURS AVAILABLE



Sabbia



Calce



Luca



Acciaio



Piombo

Group
Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	≤ 0.5 %
Breaking strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of rupture	ISO 10545-4	Ave Minimum ≥ 35 N/mm2	Ave ≥ 35 N/mm2
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	≤175mm2	≤150mm2
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	Class UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	UHB
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
BOOM STRUCTURED 600x600	✓	✓

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential