

PARKSIDE

VALLE

STONE EFFECT GLAZED PORCELAIN



3

COLOURS

2

SIZES

1


FINISH

0


SPECIAL PIECES

Inspired by slate found in the Dalradian rocks on the Isle of Arran, Valle has a natural stone look achieved using the latest printing technology. Each colour features 15 variations to give it its realistic appearance.


COLOURS AVAILABLE



Grey




Coal



Ivory

SIZE GUIDE

750x750mm



1000x500mm





Dimensions	Multiple
Finish	Matt
Body	Porcelain
Wall/Floor	Wall & Floor
Interior/Exterior	Interior & Exterior
Group	Bl _a
Pendulum Dry	TBC
Pendulum Wet	TBC

Available Sizes		Standard	Requirement	Typical Test Value
750x750x7mm 500x1000x7mm	Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
	Thickness	ISO 10545-2	$\pm 5\%$ $\leq \pm 0.5\text{mm}$	Pass
	Straightness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 1.5\text{mm}$	Pass
	Flatness	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
	Rectangularity	ISO 10545-2	$\pm 0.5\%$ $\leq \pm 2.0\text{mm}$	Pass
	Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
	Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
	Modulus of rupture	ISO 10545-4	35 N/mm ² Average min	Pass
	Resistance to surface abrasion	ISO 10545-7	n/a	PEI 3
	Frost Resistance	ISO 10545-12	Complies with Standard	Pass
	Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
	Resistance to Stain	ISO 10545-14	Min class 3	Pass
	Resistance to chemicals	ISO 10545-14	Min Class B	Pass
	Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential