

PARKSIDE

DELANO

MARBLE EFFECT PORCELAIN RANGE



2

COLOURS

3

SIZES

1

FINISH


0

SPECIAL PIECES


Delano is a marble effect porcelain tile that is reminiscent of an Art Deco Miami hotel foyer. Delano will bring a sophisticated vibe to walls and floors in one of three sizes - 300x600, 600x600 and 600x1200mm.

This range has 0% recycled content.

COLOURS AVAILABLE



CALACATTA



MARQUINA

PORCELAIN	9mm Thick	Wall/Floor
	Polished	All Tiles
300x600	✓	Wall & Floor
600x600	✓	Wall & Floor
600x1200	✓	Wall & Floor

Group

Bla – Porcelain

	Standard	Requirement	Established Values
Length & Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	Eb ≤ 0.5 %	Ave 0.1 %
Breaking strength	ISO 10545-4	≥ 1300N	Ave 1781 N
NModulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm2	Ave 41 N/mm2
Resistance to surface abrasion	ISO 10545-7	Declare Class	PEI 3
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	Class GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire	-	Class A1 A1/FL	A1 A1/FL

Recycled Content	%
Delano	0%

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential