

PARKSIDE

REIS

INDOOR/OUTDOOR PORCELAIN RANGE



7

COLOURS

1

SIZE

1


FINISH

0

SPECIAL PIECES

Reis is an innovative collection of porcelain tiles, available in 12 neutral colours. Reis offer all designs in both an indoor and outdoor option, allowing a seamless transition. With an identical surface finish to the 10mm indoor tile, the Reis 40mm outdoor tile features a layer of unique Serafoam. This creates a simple to lay system making it quicker and easier to create a seamless finish.

COLOURS AVAILABLE



Grey




Putty



Black



Light Grey



Vanilla



Walnut



Oak

SIZE GUIDE

600x600mm



PARKSIDE

PRODUCT DATA SHEET

REIS INDOOR



Dimensions	600x600x10mm
Finish	Matt
Body	Pressed Porcelain
Wall/Floor	Wall & Floor
Interior/ Exterior	Interior
Group	Bi _a
Pendulum Dry (4S)	36+
Pendulum Wet (4S)	0-24
Pendulum Wet (TRL)	0-24

Available Sizes	Standard	Requirement	Typical Test Value
600x600x10mm			
Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
Thickness	ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
Straightness	ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
Flatness	ISO 10545-2	$\pm 0.5\% \leq \pm 2.0\text{mm}$	Pass
Rectangularity	ISO 10545-2	$\pm 0.5\% \leq \pm 2.0\text{mm}$	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
Modulus of rupture	ISO 10545-4	35 N/mm ² Average min	Pass
Resistance to surface abrasion	ISO 10545-7	n/a	PEI 4
Frost Resistance	ISO 10545-12	Complies with Standard	Pass
Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
Resistance to Stain	ISO 10545-14	Min class 3	Pass
Resistance to chemicals	ISO 10545-14	Min Class B	Pass
Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

PARKSIDE

PRODUCT DATA SHEET



REIS OUTDOOR

Dimensions	600x600x40mm
Finish	Matt
Body	Pressed Porcelain
Wall/Floor	Wall & Floor
Interior/ Exterior	Exterior
Group	Bl _a
Pendulum Dry (4S)	36+
Pendulum Wet (4S)	36+
Pendulum Wet (TRL)	36+

Available Sizes

600x600x40mm

INFO:

The Reis Serafoam base is made up of a 30mm layer of aerated porcelain attached to the bottom of the 10mm pressed porcelain tile.

	Standard	Requirement	Typical Test Value
Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
Thickness	ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
Straightness	ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
Flatness	ISO 10545-2	$\pm 0.5\% \leq \pm 2.0\text{mm}$	Pass
Rectangularity	ISO 10545-2	$\pm 0.5\% \leq \pm 2.0\text{mm}$	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
Modulus of rupture	ISO 10545-4	35 N/mm ² Average min	Pass
Resistance to surface abrasion	ISO 10545-7	n/a	PEI 4
Frost Resistance	ISO 10545-12	Complies with Standard	Pass
Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
Resistance to Stain	ISO 10545-14	Min class 3	Pass
Resistance to chemicals	ISO 10545-14	Min Class B	Pass
Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass
SERAFOAM BASE			
Thermal Shock Resistance	ISO 10549-9	Complies with Standard	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Bending Strength	ISO 10545		Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value.

Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential