

Group	Luxury Vinyl Flooring Rigid Tile 61cm x 30.5cm
--------------	--

	Standard	Result
CE/DOP	BS EN 14041	Pass
Usage Classification	BS EN 485	23-31
Manufacturing Standard	BS EN 649	Pass
Total Thickness	BS EN 428	6 mm
Wear Layer thickness	BS EN 429	0.3mm
Weight	BS EN 430	8.11 kg/m ²
Abrasion Resistance	BS EN 660-1/2	Group T
Residual Indentation	BS EN 433	Pass
Dimensional Stability	BS EN 434	Pass
Chemical Resistance	BS EN 423	Pass
Colour Fastness to Light	BS EN 20105-B02	≥ 6 Class
Flammability	BS EN 13501-1-1 Class Bfl-S1	Pass
Caster Chair Resistance	BS EN 425	22034
Impact Sound Insulation	BS EN ISO 140-8	IIC=73 STC=72
Thermal Resistance	BS EN 12667	0.033(m ² .k)/W
Electrostatic Performance	BS EN 1815	0.2 Kv
Emissions	Floor Score	Pass
Phthalate Free	BS EN 14372	Pass

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
Full Range	✓	✓

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

Group

Luxury Vinyl Flooring Rigid Plank 123cm x 17.9cm

	Standard	Result
CE/DOP	BS EN 14041	Pass
Usage Classification	BS EN 485	23-31
Manufacturing Standard	BS EN 649	Pass
Total Thickness	BS EN 428	6 mm
Wear Layer thickness	BS EN 429	0.3mm
Weight	BS EN 430	9.83 kg/m ²
Abrasion Resistance	BS EN 660-1/2	Group T
Residual Indentation	BS EN 433	Pass
Dimensional Stability	BS EN 434	Pass
Chemical Resistance	BS EN 423	Pass
Colour Fastness to Light	BS EN 20105-B02	≥ 6 Class
Flammability	BS EN 13501-1-1 Class Bfl-S1	Pass
Caster Chair Resistance	BS EN 425	25322
Impact Sound Insulation	BS EN ISO 140-8	IIC=73 STC=72
Thermal Resistance	BS EN 12667	0.033(m ² .k)/W
Electrostatic Performance	BS EN 1815	0.2 Kv
Emissions	Floor Score	Pass
Phthalate Free	BS EN 14372	Pass

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
Full Range	✓	✓

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

Group	Luxury Vinyl Flooring Rigid Plank 121.8cm x 22.6cm
--------------	--

	Standard	Result
CE/DOP	BS EN 14041	Pass
Usage Classification	BS EN 485	31-34
Manufacturing Standard	BS EN 649	Pass
Total Thickness	BS EN 428	5mm
Wear Layer thickness	BS EN 429	0.5mm
Weight	BS EN 430	7.68 kg/m ²
Abrasion Resistance	BS EN 660-1/2	Group T
Residual Indentation	BS EN 433	Pass
Dimensional Stability	BS EN 434	Pass
Chemical Resistance	BS EN 423	Pass
Colour Fastness to Light	BS EN 20105-B02	≥ 6 Class
Flammability	BS EN 13501-1-1 Class Bfl-S1	Pass
Caster Chair Resistance	BS EN 425	22130
Impact Sound Insulation	BS EN ISO 140-8	IIC=55 STC=49
Thermal Resistance	BS EN 12667	0.033(m ² .k)/W
Electrostatic Performance	BS EN 1815	0.2 Kv
Emissions	Floor Score	Pass
Phthalate Free	BS EN 14372	Pass

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
Full Range	✓	✓

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential