

Extract Quarry

5 COLOURS / 1 SIZE / 1 FINISH

With their strong reds, browns and blacks and dark shade variations evocative of tiles fired in bygone kilns, these tiles are conceived to help create outdoor areas with an elegant traditional allure.


Quarry's 15x15cm tiles can be used to pave terraces, balconies, entrance stairways, verandas or rooftops, guaranteeing top-quality attention to detail thanks to the series' accompanying special tile pieces, which include stair tread corners, skirtings and pool coping.



Extract Quarry



Quarry	12mm thick	Wall/floor	Interior/exterior
	Matt	All tiles	All tiles
150x150	✓	Wall & Floor	Interior & Exterior



150x150x12



The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles

Extract Quarry Tiles

GROUP / Alla-2 – Extruded Ceramic

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±1.5%(Max 2mm)	Conforms
Thickness	ISO 10545-2	±10%	Conforms
Straightness	ISO 10545-2	±0.5%	Conforms
Flatness	ISO 10545-2	±0.8%	Conforms
Rectangularity	ISO 10545-2	±1%	Conforms
Water Absorption	ISO 10545-3	Eb 3% ≤ 0.5%	4.2%
Breaking Strength	ISO 10545-4	≥ 800N	2350N
Modulus of Rupture	ISO 10545-4	Ave Minimum 13 N/mm ²	Ave Minimum 25 N/mm ²
Resistance to deep Abrasion	ISO 10545-6	≤541mm ³	≤541mm ³
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Moisture Expansion	ISO 10545-10	Declare result	<0.1mm/m
Crazing Resistance	ISO 10545-11	Declare result	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to Stain	ISO 10545-14	Min Class 3	Min Class 3
Reaction to Fire		Class A1 A1/FL	A1 A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36	Pendulum Wet (4S Slider 96) +36
Full Range	√	√

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles