

Monroe Brick

8 COLOURS / 2 SIZES / 1 FINISHES / 0 SPECIAL PIECES

The Monroe range is made to please the most demanding designers and architects, with a combination of concrete, gloss, wood and mosaic options. The most extraordinary combinations can be created thanks to the assortment of 8 colour variations, 4 warm tones and 4 cold – different patterns are never repeated over around 10m² of product, producing original design schemes.



Monroe Brick



Monroe Brick



WHITE GLOSS WALL



IVORY GLOSS WALL



SAND GLOSS WALL



GREY GLOSS WALL



SMOKE GLOSS WALL



TAUPE GLOSS WALL



BROWN GLOSS WALL




BLACK GLOSS WALL



PURE WHITE GLOSS WALL

Monroe Brick



60x250



125x250

GROUP / Bla - PORCELAIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	$E_b \leq 0.5\%$	Ave 0.5%
Breaking strength	ISO 10545-4	$\geq 1300N$	Ave $\geq 2000N$
Modulus of rupture	ISO 10545-4	Ave min 35 N/mm ²	Ave min 45 N/mm ²
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm ²	Ave 175mm ³
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare value	UHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare value	ULA
Resistance to stain	ISO 10545-14	Declare value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

Recycled content	%
Monroe Brick	12

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles