Entic

1 COLOURS / 4 SIZES / 4 FINISHES / 0 SPECIAL PIECES

The marked character of original and prestigious wood essences breathes new life on the surface of extremely natural and elegant porcelain tiles, for indoor and outdoor areas with cutting edge design. With a pleasant sense of motion, the surface is characterised by outstanding graphic depth that evokes, with extraordinary realism and authenticity, the alluring details of original planks of wood. Outdoor 20mm available in 300x1200 Recycled content: 20% apart from Ecal Matt 225x900 and 150x900 which are 40%.





Entic







EUCALI SMOKE



QUERCIA ANTIQUE 20MM

ROVERE VENICE





EUCALI SMOKE 20MM



ROVERE VENICE 20MM

NOCE HICKORY 20MM

Porcelain		<u>.</u>		·	Wall/floor	Interior/exterior
	Matt	Grip	Slip resistant	Structured		
150x900						
225x900						
250x1500						
300x1200						

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk

Entic

 300x1200	225x900	150x900

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	E _b > 0.5%	Ave ≤ 0.1%
Breaking strength	ISO 10545-4	≥ 1300N	9mm - Ave 1500N & 20mm - 10000N
Modulus of rupture	ISO 10545-4	Ave min 35 N/mm ²	Ave 40 N/mm ²
Resistance to deep abrasion	ISO 10545-7	Declare Class	Grey & Dark Beige - PEI 3. White & Brown - PEI
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire -		Class A1 A1/FL	A1 A1/FL

Slip resistance characteristics	Pendulum Dry (4S Slider 96)	Pendulum Wet (4S Slider 96)	Recycled content	%
	+36 PTV	+36 PTV	Entic	20-29
Full range	√	✓		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk