

Fairhurst

7 COLOURS / 4 SIZES / 1 FINISHES / 0 SPECIAL PIECES

A wood effect collection featuring an exquisite grained design, Fairhurst is available in 7 colours on a spectrum of warm and cool shades, giving an option for any scheme. The finish stands out for its slip resistant properties and luxurious smooth feel. This range has 37% recycled content.



Fairhurst



Fairhurst



Fairhurst



WHITE



WHITE STRIPES



WHITE TANGRAM



WHITE CHEVRON



ASH



ASH STRIPES



ASH TANGRAM



ASH CHEVRON



MAPLE



MAPLE STRIPES



MAPLE TANGRAM



MAPLE CHEVRON



TAUPE



TAUPE STRIPES



TAUPE TANGRAM



TAUPE CHEVRON

Fairhurst



HONEY



HONEY STRIPES



HONEY TANGRAM



HONEY CHEVRON



SMOKE



SMOKE STRIPES



SMOKE TANGRAM



SMOKE CHEVRON



WALNUT



WALNUT STRIPES



WALNUT TANGRAM



WALNUT CHEVRON

Porcelain	11mm thick	Wall/floor
	Matt	All tiles
1510x240 (Plank)	✓	Wall and floor
320x286 (Chevron)	✓	Wall and floor
300x300 (Tangram)	✓	Wall and floor
750x240 (Stripes)	✓	Wall and floor

*Only available in Sand and Argent

Fairhurst

GROUP / Bla - PORCELAIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	$E_b \leq 0.5\%$	Ave $\leq 0.5\%$
Breaking strength	ISO 10545-4	$\geq 1300N$	$\geq 1300N$
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	Ave min 35 N/mm ²
Resistance to surface abrasion	ISO 10545-7	Declare Class	Taupe, Honey, Walnut & Smoke – PEI 3 Ash, Maple & White – PEI 4
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

Slip resistance characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
Full range	✓	✓

Recycled content	%
Fairhurst	37

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles