
# Hopper


#### 3 COLOURS / 4 SIZES / 2 FINISHES / 0 SPECIAL PIECES

Out of nostalgia for terrazzo and passion for the Mediterranean comes this collection of peaceful and quiet colours that seeks to capture the emotion of the sea through sand and seashells. A concept that shows us how to conceive new materials linked to the nature of the environment, aesthetics in balance and timelessness. Available in various sizes including mosaics, the natural finish of Fragments brings a stylish and calming feel to any space.









## Hopper





WHITE MATT

WHITE SEMI POLISHED





GREY MATT

GREY SEMI POLISHED





BLACK MATT


BLACK SEMI POLISHED

| Porcelain | 10.5mm thick | Wall/floor    | Wall/floor     |
|-----------|--------------|---------------|----------------|
|           | Matt         | Semi polished | All tiles      |
| 300x600   | ✓            | <b>√</b>      | Wall and floor |
| 600x600   | ✓            | ✓             | Wall and floor |
| 600x1200  | ✓            | ✓             | Wall and floor |
| 1200x1200 | ✓            | ✓             | Wall and floor |

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk

## Hopper



### GROUP / Bla - PORCELAIN

|   | Standard     | Requirement                      | Established values |
|---|--------------|----------------------------------|--------------------|
| Length and width  | ISO 10545-2  | ±0.6% ~ ±2mm                     | Conforms           |
| Thickness   | ISO 10545-2  | ±5% ~ ±0.5mm                     | Conforms           |
| Straightness  | ISO 10545-2  | ±0.5% ~ ±1.5mm                   | Conforms           |
| Flatness  | ISO 10545-2  | ±0.5% ~ ±2.0mm                   | Conforms           |
| Rectangularity  | ISO 10545-2  | ±0.5% ~ ±2.0mm                   | Conforms           |
| Water absorption  | ISO 10545-3  | E <sub>b</sub> ≤ 0.5%            | Ave ≤ 0.1%         |
| Breaking strength   | ISO 10545-4  | ≥ 1300N                          | Ave 6500N          |
| Modulus of rupture  | ISO 10545-4  | Ave Minimum 35 N/mm²             | Ave min 45 N/mm²   |
| Resistance to deep abrasion                               | ISO 10545-6  | ≤ 175mm²                         | Ave ≤ 140mm²       |
| Thermal shock resistance                                  | ISO 10545-9  | Pass according to EN ISO 10545-1 | Resistant          |
| Frost resistance  | ISO 10545-12 | Pass according to EN ISO 10545-1 | Resistant          |
| Resistance to household chemicals and swimming pool salts | ISO 10545-13 | Min Class UB                     | UA                 |
| Resistance to high concentrations of alkalis and acids    | ISO 10545-13 | Declare Value                    | UHB                |
| Resistance to low concentrations of alkalis and acids     | ISO 10545-13 | Declare Value                    | ULB                |
| Resistance to stain                                       | ISO 10545-14 | Declare Value                    | Class 5            |
| Reaction to fire  | -            | Class A1 A1/FL                   | A1 A1/FL           |

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.