Puzzle Pattern


8 COLOURS / 1 SIZES / 1 FINISHES / 0 SPECIAL PIECES

Designed by Edward Barber and Jay Osgerby for Mutina, Puzzle Pattern is a mixture of block colours and multi-coloured graphic patterns.









Puzzle Pattern



The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

Puzzle Pattern



GROUP / Bla - PORCELAIN

| | Standard | Requirement | Established values |
|---|--------------|----------------------------------|---|
| Length and width | ISO 10545-2 | ±0.6% ~ ±2mm | Conforms |
| Thickness | ISO 10545-2 | ±5% ~ ±0.5mm | Conforms |
| Straightness | ISO 10545-2 | ±0.5% ~ ±1.5mm | Conforms |
| Flatness | ISO 10545-2 | ±0.5% ~ ±2.0mm | Conforms |
| Rectangularity | ISO 10545-2 | ±0.5% ~ ±2.0mm | Conforms |
| Water absorption | ISO 10545-3 | E _b ≤ 0.5% | Ave 0.06% |
| Breaking strength | ISO 10545-4 | ≥ 1300N | ≥ 1300N |
| Modulus of rupture | ISO 10545-4 | Ave min 35 N/mm² | Ave min 35 N/mm² |
| Resistance to surface abrasion | ISO 10545-7 | Declare Class | Anglesley, Milos, Faroe, Skye, Murano & Creta – PEI 3 Gotland & Aland – PEI 4 |
| Thermal shock resistance | ISO 10545-9 | Pass according to EN ISO 10545-1 | Resistant |
| Frost resistance | ISO 10545-12 | Pass according to EN ISO 10545-1 | Resistant |
| Resistance to household chemicals and swimming pool salts | ISO 10545-13 | Min Class GB | GA |
| Resistance to high concentrations of alkalis and acids | ISO 10545-13 | Declare Value | GHA |
| Resistance to low concentrations of alkalis and acids | ISO 10545-13 | Declare Value | GLA |
| Resistance to stain | ISO 10545-14 | Declare Value | Class 5 |
| Reaction to fire | - | Class A1 A1/FL | A1 A1/FL |

| Recycled content | % |
|------------------|----|
| Puzzle | 20 |

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk