

### 5 COLOURS / 6 SIZES / 2 FINISHES / 0 SPECIAL PIECES

Inspired by the different textures of earth, the stone effect Sensi range has been designed by Italian architect and designer Matteo Thun. Available in five neutral shades, the collection remind us of the strength of nature. Developed with close attention to environmental impact, Sensi uses recycled content and sustainable production processes with self-generated electricity and water recycling.










The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential



Porcelain	10mm thick				6mm thick			
	Dust - Matt	Sand - Matt	Lithos - Bush hammer	Fossil - Matt	Dust - Matt	Sand - Matt	Lithos - Bush hammer	Fossil - Matt
600×1200	✓	<b>─</b>	<u> </u>	<u> </u>	✓	✓		
800x800	✓	<b>─</b>	✓	<b>√</b>				
400x800	✓	<u> </u>	✓	<b>√</b>				
1200x1200					✓	✓		_ ✓
200x2400					✓	<b>√</b>		
200x2800					✓			

Porcelain	20mm thick	20mm thick Wall/floor Interior/exterior			
	Sand - Structured	All tiles	All tiles		
600x1200	✓	Wall and floor	Interior & exterior		
800x800		Wall and floor	Interior & exterior		
400x800		Wall and floor	Interior & exterior		
1200x1200		Wall and floor	Interior & exterior		
1200x2400		Wall and floor	Interior & exterior		
1200x2800		Wall and floor	Interior & exterior		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

GROUP / Bla - PORCELAIN SENSI – 20MM

Range	Standard	Requirement	Established Values	
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms	
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms	
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms	
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Water absorption	ISO 10545-3	E <sub>b</sub> ≤ 0.5%	Ave 0.08%	
Breaking strength	ISO 10545-4	≥ 1300N	14000N	
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm²	Ave 52 N/mm²	
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm³	Ave 140mm <sup>3</sup>	
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant	
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant	
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA	
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD	
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA	
Resistance to stain	ISO 10545-14	Declare Value	Class 4	
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL	

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

GROUP / Bla - PORCELAIN SENSI – 10MM

Range	Standard	Requirement	Established Values	
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms	
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms	
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms	
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Water absorption	ISO 10545-3	E <sub>b</sub> ≤ 0.5%	Ave 0.08%	
Breaking strength	ISO 10545-4	≥ 1300N	14000N	
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm²	Ave 52 N/mm²	
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm³	Ave 140mm <sup>3</sup>	
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant	
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant	
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA	
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD	
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA	
Resistance to stain	ISO 10545-14	Declare Value	Class 4	
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL	

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

GROUP / Bla - PORCELAIN SENSI – 6MM

Range	Standard	Requirement	Established Values	
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms	
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms	
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms	
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Water absorption	ISO 10545-3	Eb ≤ 0.5%	Ave 0.08%	
Breaking strength	ISO 10545-4	≥ 1300N	≥ 1350N	
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm2	Ave 52 N/mm2	
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm3	Ave 140mm3	
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant	
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant	
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA	
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD	
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA	
Resistance to stain	ISO 10545-14	Declare Value	MATTE - Class 5 LITHOS & SAND - Class 4	
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL	

Recycled content	%
10mm Brown and Grey	41.9
10mm Taupe	12.7
10mm Ivory and White	7.1
20mm options	12.5
6mm slabs	7.1

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential