# Shimla+

#### 7 COLOURS / 1 SIZES / 2 FINISHES / 0 SPECIAL PIECES

Seven pre-scored patterned tiles that will create the impression of an encaustic floor often found in townhouses. We love the detailed borders available within the range. This collection has 7% recycled content.







# Shimla+





GATZBY

AMBERLEY ORCHID





BERKELEY ESSENCE GRAPHITE

BERKELEY ESSENCE SKY






BERKELEY ESSENCE EDEN

AMBERLEY PINK

Porcelain	10mm thick	Wall/floor	Interior/exterior	
	Matt	All tiles	All tiles	
452x452	✓	Wall and floor	Interior and exterior	

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential

### Shimla+



#### GROUP / Bla - PORCELAIN

Range	Standard	Requirement	Established Values	
Length and width	ISO 10545-2	+0.6% ~ +2mm	Conforms	
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms	
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms	
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms	
Water absorption	ISO 10545-3	E <sub>b</sub> ≤ 0.5%	Ave 0.5%	
Breaking strength	ISO 10545-4	≥ 1300N	Ave ≥ 1300N	
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm²	Ave 35 N/mm²	
Resistance to deep abrasion	ISO 10545-7	Declare Class	Stello Black – PEI 3 & Full range – PEI 4	
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant	
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant	
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA	
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA	
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA	
Resistance to stain	ISO 10545-14	Declare Value	Class 5	
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL	

## Grout and trim available

	Pendulum Dry (4S Slider 96)	Pendulum Wet (4S Slider 96)	_	Shimla+	Grout	Trim
	+36 PTV	+36 PTV				
			-			
	<u> </u>	· · · · · · · · · · · · · · · · · · ·	_			
Recycled content	%					
Shimla+	36					

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential