

3 COLOURS / 1 SIZES / 1 FINISHES / 0 SPECIAL PIECES

YVE evokes a historic collection. A semi-matt surface in 3 colours - Bianco, Nero and Blu, and tone on tone brush-strokes rediscover the beauty of the majolica tiles typical of Mediterranean architecture. This range has 12% recycled content.






















BLU TAPPETO 2A



BLU TAPPETO 2B





NERO TAPPETO 2B



BIANCO





NERO DECOR MIX



For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk

GROUP / Bla - PORCELAIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking strength	ISO 10545-4	≥ 1300N	Ave >1300N
Modulus of rupture	ISO 10545-4	Ave min 35 N/mm²	Ave min 35 N/mm ²
Resistance to deep abrasion (unglazed tiles)	ISO 10545-6	<175mm ²	Ave 175mm ³
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	UHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULB
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk