


## Zellige

## 12 COLOURS / 1 SIZES / 1 FINISHES / 3 SPECIAL PIECES

North African tradition meets industrial ceramics. The hand-crafted look tiles in the Zellige series are produced in 12 shades with glossy finish and visible variations in tone. Random installation creates a blend effect, in which the colours vibrate strongly.







## Zellige



GESSO







ARGILLA



SALVIA

BOSCO



CORALLO

CAMMELO



CIELO



TURCHESE





CARBONE



CARBONE MOSIAC








BOSCO MOSIAC

Ceramic	10mm	Wall/floor	Interior/exterior
	Gloss	All tiles	All tiles
100x100	~	Wall	Interior
300x300 Mosaic	~	Wall	Interior

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk



## GROUP / Bla - CERAMIC

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.5% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±10% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.3% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	3% E <sub>b</sub> Individual maximum < 6%	Ave < 6%
Breaking strength	ISO 10545-4	≥ 1000N	≥ 1000N
Modulus of rupture	ISO 10545-4	Ave min 20 N/mm <sup>2</sup>	Ave min 22 N/mm <sup>2</sup>
Thermal shock resistance	ISO 10545-1	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

Recycled content	%
Zellige	10

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk