# Tyne

#### 4 COLOURS / 1 SIZE / 1 FINISH

Resembling brickwork from Tribeca, Manhattan, Tyne lends your space a stylish industrial look that's infused with a sense of luxurious modern living. A versatile choice, these matt rectangular porcelain tiles can be used inside and outside, on floors as well as walls. Tyne is rated PTV+36 and has 50% recycled content.







## Tyne





WHITE GREY





SAND RED

	10mm thick	Wall/floor	Interior/exterior
Porcelain	Matt	All tiles	All tiles
60x250	~	Wall & Floor	Interior & Exterior

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W:  $\underline{www.parkside.co.uk} - E: \underline{info@parkside.co.uk}$ 

## Tyne

#### GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E <sub>b</sub> ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm <sup>2</sup>	46 N/mm2
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	PEI 5
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire		Class A1 A1/FL	Class A1 A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36	Pendulum Wet (4S Slider 96) +36	Pendulum Wet (TRL Slider 55) +36
Full Range	<b>√</b>	✓	✓

Recycled Content	50 %
Range Name	Tyne

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.