# Adger

#### 11 COLOURS / 1 SIZES / 2 FINISHES / 0 SPECIAL PIECES

Adger brings a multitude of colours in a bevelled metro brick that can be laid in a variety of patterns with a contrasting grout for an on trend look. 11 colours are available, all in 100x200mm.







### Adger



The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk

## Adger



#### 200x100

Dimensions	100x200x8mm	
Dimensions		
Finish	Gloss and matt	
Body	Ceramic	
Wall/floor	Wall	
Group	BIII	
Pendulum Dry	-	
Pendulum Wet	-	
Recycled content	-	

	Standard	Requirement	Typical test value
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Pass
Thickness	ISO 10545-2	±10% ~ ±0.5mm	Pass
Straightness	ISO 10545-2	±0.3% ~ ±1.5mm	Pass
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Pass
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Pass
Water absorption	ISO 10545-3	$E_{b} \leq 10\%$	Pass
Breaking strength	ISO 10545-4	≥ 600N	Pass
Modulus of rupture	ISO 10545-4	Ave Minimum 12 N/mm <sup>2</sup>	Pass
Resistance to surface abrasion	ISO 10545-7	n/a	n/a
Thermal shock resistance	ISO 10545-9	Complies with standard	Pass
Frost resistance	ISO 10545-12	Complies with standard	Not resistant
Resistance to chemicals	ISO 10545-13	Min Class B	Pass
Resistance to stain	ISO 10545-14	Min Class 3	Pass
Reaction to fire	-	Floor/wall Class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 - W: www.parkside.co.uk - E: info@parkside.co.uk