

Alicante

8 COLOURS / 8 SIZES / 2 FINISHES / 4 SPECIAL PIECES

Alicante replicates traditional terracotta floors, reminiscent of the sunshine of Spain. Glazed shapes and tacos add more flexibility in design and allows for a pop of colour against the base tile. With a PTV+36 finish, Alicante is great for use outdoors, including around a swimming pool.



Alicante



PALERMO



VERONA



FERRARA



COTTO CROSS



FORESTA CROSS



BIANCO CROSS




VERONA / FERRARA LOSANGA



COTTO / FORESTA ARROW



BIANCO STRIP



VERDE STRIP



BLU STRIP



AQUAMARINE STRIP



BIANCO ARROW




VERDE ARROW




AQUAMARINE ARROW




BIANCO STAR



VERDE STAR



BLUE STAR




AQUAMARINE STAR



BIANCO SQUARE / TACO



VERDE SQUARE / TACO



BLU SQUARE / TACO



AQUAMARINE SQUARE / TACO

Porcelain	10mm thick	10mm thick	Wall/floor	Interior/exterior
	Matt	Glazed	All tiles	All tiles
225x225	✓		Wall & Floor	Interior & Exterior
225x450	✓		Wall & Floor	Interior & Exterior
450x450	✓		Wall & Floor	Interior & Exterior
180x450	✓		Wall & Floor	Interior & Exterior
18x18 Cross	✓	✓	Wall & Floor	Interior & Exterior
74x480 Arrow	✓	✓	Wall & Floor	Interior & Exterior
40x40 Taco		✓	Wall & Floor	Interior & Exterior
150x150 Square		✓	Wall & Floor	Interior & Exterior
150x450 Strip		✓	Wall & Floor	Interior & Exterior

Alicante

GROUP / A1a – EXTRUDED PORCELAIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±2.0% to max 4mm	Conforms
Thickness	ISO 10545-2	±10%	Conforms
Straightness	ISO 10545-2	±0.6%	Conforms
Flatness	ISO 10545-2	±1.5%	Conforms
Rectangularity	ISO 10545-2	±1.0%	Conforms
Water absorption	ISO 10545-3	$E_b \leq 0.5\%$	Ave $\leq 0.5\%$
Breaking strength	ISO 10545-4	$\geq 1300N$	$\geq 2200N$
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	Ave 35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare value	PEI – 3
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire		Class A1 A1/FL	Class A1 A1/FL

Slip resistance characteristics	Pendulum Dry (4S Slider 96) +36 PTV	Pendulum Wet (4S Slider 96) +36 PTV
Grip Finish only	✓	✓

Recycled content	%
Alicante	0

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles