

4 COLOURS / 1 SIZE / 1 FINISH / 0 SPECIAL PIECES


With concrete and colour mixes a key interior design trend, this exclusive Group range offers a stylish geometric design in a mixed matt and gloss finish. Taking inspiration from Art Revival, these four trend led colours bring a touch of decorative art to any space.
















	7mm thick	Wall/floor	Interior/exterior
Porcelain	Matt & Gloss	All tiles	All tiles

Wall & Floor

200x200x7

Laying Pattern Ideas

200x200



Interior

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: $\underline{www.parkside.co.uk} - E: \underline{info@parkside.co.uk}$

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	E _b ≤ 0.5%	Ave ≤ 0.5%
Breaking strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm²	Ave 35 N/mm²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare value	PEI -3
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Min Class 3
Reaction to fire		Class A1 A1/FL	A1 A1/FL

Recycled content	%
Fenchurch	14

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.