TECHNICAL INFO

CREATING



OUTDOOR PORCELAIN

YOUR SPACE. YOUR WAY.

Everscape[™] is a range of specialised 2cm deep outdoor tiles with an amalgamation of 'FOREVER' and 'LANDSCAPE' embodied in its spirit.

This combination of elegant, simple design married with innovative technology allows you to make a real improvement to your outdoor space for years to come.

Extend your style outside and love your garden all year round!

ESCAPE AND ENJOY From sun drenched patios and secret courtyard gardens to cosy city balconies and breezy beachfront terraces, our exclusive range of outdoor tiles will help transform every corner of your home into spaces you'll never want to leave; creating the perfect space for endless summers.

PORCELAIN

Porcelain is stain, fire and frost resistant, meaning little upkeep is needed, and with multiple ways to fit Everscape[™], its an easy DIY solution for the budding landscape designer in all of us.

The 2cm depth coupled with the slip resistant surface provides ultimate durability for your outdoor space.

RESILIENT YET ELEGANT



Everscape™ vs Traditional Slabs

Everscape[™] offers a clean-cut edge for uniformity, and unlike traditional paving slabs, Everscape[™] features a hardwearing finish available in a choice of colours and designs which are resistant to fading and staining.

This makes Everscape[™] quick and easy to clean.

For that summer refresh, all you need is a power washer and a suitable outdoor cleaner such as FILA Outdoor Patio and Porcelain Cleaner.





The Enis range mixes the classic texture of slate with a modern colour palette to revamp any outdoor space. The rustic nature of the slate effect pairs perfectly with soft greenery and slow-moving water.

AVAILABILITY



Everscape Enis


GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	> 35 N/mm2
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	NPD
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance Pendulum Dry		Pendulum Wet	Recycled Content	5 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Enis
Full Range	~	~		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE[™] - VALLETTA



The Valletta range is available in two contemporary colours that expertly mimic natural stone. The variety of sizes allows you to fill your space in a laying pattern of your choosing and with a multitude of fixing options, you can put your patio anywhere in the garden.



Everscape Valletta

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	Class 3
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance Pendulum Dry		Pendulum Wet	Recycled Content	0 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Valletta
Full Range	~	~		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.



The Homestone range is available in 2 natural colourways that expertly replicate natural stone and are inspired by the landscape of the seacoast. More hardwearing and durable than natural stone, this porcelain tile has a finish which is resistant to fading and staining.



Everscape Homestone

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	PEI IV
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry	Pendulum Wet	Recycled Content	0 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Homestone
Full Range	~	✓		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE™ - KEMBLE



Create a modern yet timeless aesthetic with the Kemble tile.

Kemble is a soft limestone effect with minimal patterning that mimics natural stone and is available in three warm shades.



Everscape Kemble

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire		Class A1 A1/FL	Class A1/FL

	Pendulum Wet	Recycled Content	5 %	
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Kemble
Full Range	~	✓		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE™ - RIVEN





2cm Thickness




Resistance



Stain Resistant



Suitable For Outdoor



MIMICS NATURAL STONE

59.2 x 59.2cm

Introduce this Riven grey stone effect paving into your garden for a luxury feel whilst on a budget.

The Riven range brings together modernity and safety with its slip resistant finish and resistance to fading and staining.







Per Box



2.83 Tiles Per M²






COLOURS



GRAPHITE



GREY

Everscape Riven

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	> 35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	Class 2
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry	Pendulum Wet	Recycled Content	0 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Riven
Full Range	~	✓		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE™ - SANDSTONE



The sandstone effect range is available in traditional beige but also a contemporary grey that really highlights the unique markings of the natural stone, expertly replicated on vitrified porcelain.

This hardy base makes the Everscape[™] range durable and stain resistant.

Coupled with its slip resistance and hard wearing finish, Everscape[™] Sandstone is an ideal choice for your patio.

COLOURS



Everscape Sandstone

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	Class 3
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Declare Value	Class 5
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry	Pendulum Wet	Recycled Content	0 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Sandstone
Full Range	~	✓		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.



The Everscape[™] planks wood effect range, available in Oak and Grey, offers an easy maintenance solution to decking.

Traditional wooden decking needs to be maintained over the years with consistent staining and will eventually rot away, not only this, but it can become very slippery in wet weather conditions.

The vitrified porcelain of Everscape[™] is hardwearing and resistant to staining, plus the laser printed finish prevents colour fading in direct sunlight; coupled with a high slip resistance makes Everscape[™] Planks the perfect upgrade to regular garden decking.

COLOURS



GREY



OAK





1 Tile Per Box



Tiles Per M²

AVAILABILITY

29.5 x 120cm

Everscape Planks

GROUP / BLa - PORCELAIN


	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm²
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry	Pendulum Wet	Recycled Content	0 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Planks
Full Range	~	~		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE™ - GRANITE

Create a natural feeling granite finish to your outdoor pathway or patio with the knowledge that this porcelain tile is hardier and more durable than natural stone.



Everscape Granite

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry		Recycled Content	0 %
Characteristics	(4S Slider 96) +36		Range Name	Everscape Granite
Full Range	~	~		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE™ - CEMENTO



Resistant

High Slip

Resistance

Introduce this concrete effect porcelain paving into your garden for a luxury feel whilst on a budget.

The Cemento range brings together modernity and safety with its slip resistant finish and resistance to fading and staining.





2 Tiles Per Box **COLOURS**



TAUPE

Everscape Cemento

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	Class 3
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry	Pendulum Wet	Recycled Content	0 %
Characteristics	(4S Slider 96) +36	(4S Slider 96) +36	Range Name	Everscape Cemento
Full Range	~	~		

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE[™] - MARBSTONE & EARTHSTONE

Bring the look of natural stone to your outdoor space with our extra large porcelain Everscape[™] Marbstone or Everscape[™] Earthstone range.





Thickness



Suitable For Outdoor



Features Variation



Resistance

Stain Resistant

COLOURS



MARBSTONE



EARTHSTONE

AVAILABILITY

60 x 120cm







1 Tile Per Box



1.39 Tiles Per M²



Everscape Marbstone & Earthstone

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤ 0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	Class 3
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Slip Resistance	Pendulum Dry			Recycled Content	0 %
Characteristics	(4S Slider 96) +36		Range Name	Everscape Marbstone & Earthstone	
Full Range	4	~			

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

EVERSCAPE[™] - INTERLOCK

Utilising the technology and expertise made to create natural split face tiles, these Everscape[™] porcelain tiles are calibrated to different thicknesses to perfectly emulate the beauty of true split face.

Available in four colourways, they coordinate with other tiles in the Everscape[™] range to create a seamless and decorative finish to your outdoor space.

These interlocking porcelain wall tiles can also be used indoors for a rustic finish.





1.5 - 2cm Thickness



Suitable For Outdoor



Features Variation






Stain Resistant


Wall Only

COLOURS









MARBSTONE GREY

Please note that due to the size and thickness of Everscape[™] Interlock tiles, these exceed the load bearing weight of plaster and plasterboard substrates.

AVAILABILITY



Everscape Interlock

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	E _b ≤ 0.5%	≤0.5%
Breaking Strength	ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	35 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	Class 3
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLB
Resistance to Stain	ISO 10545-14	Declare Value	Class 3
Reaction to Fire		Class A1 A1/FL	Class A1

Recycled Content	0 %	
Range Name	Everscape Interlock	

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.