

Below

3 COLOURS / 5 SIZES / 8 FINISHES

Below is a range of eight finishes and nine sizes that redefine stone and enhance its surface. With finishes like natural, polished, bush-hammered, etched, antiqued and textured, Below offers a wide range of design choices, ideal for residential or commercial, indoor or outdoor.



Below



Below



Below



NATURAL FLAMED HAMMERED CRACK GROOVED CHEVRON POLISHED

SIZE	NATURAL	POLISHED	FLAMED	CRACK	GROOVED	HONED	HAMMERED	CHEVRON	MIX	Wall / Floor	Int / Ext
800x1800	W B									W&F	Both
800x800				G						W&F	Both
600x1200	W B G	W B G	W B G	B G	W B G	W	W B G			W&F	Both
600x600				B G		W				W&F	Both
300x600	W B G									W&F	Both
200x800								W		W&F	Both
75x1200	W B G									W&F	Both
75x600									W B G	W&F	Both
300x300 Mosaic									W B G	W&F	Both

W = White B = Beige G = Grey

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles

Below

GROUP / BLa - PORCELAIN

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water Absorption	ISO 10545-3	$E_w \leq 0.5\%$	$\leq 0.5\%$
Breaking Strength	ISO 10545-4	$\geq 1300N$	$\geq 1300N$
Modulus of Rupture	ISO 10545-4	Ave Minimum 35 N/mm ²	48 N/mm ²
Resistance to deep abrasion (glazed tiles)	ISO 10545-7	Declare Value	PEI 4
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	GHB
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to Stain	ISO 10545-14	Declare Value	Class 4
Reaction to Fire		Class A1 A1/FL	Class A1/FL

Recycled Content	0 %
Range Name	Below

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles